

# K-Mag<sup>®</sup> Special Standard

## 0-0-21.5

### Chemical Composition

Component	Symbol	Typical	Guarantee
Potassium Oxide Equivalent	K <sub>2</sub> O	21.9 %	21.5% Minimum
Magnesium	Mg	11.4 %	10.8% Minimum
Sulfur	S	22.3 %	22% Minimum
Chloride	Cl <sup>-</sup>	2.0 %	2.5% Maximum
Moisture	H <sub>2</sub> O	0.15 %	

### Particle Size Distribution Cumulative %

Tyler Mesh	US Mesh	Opening (mm)	Typical Range	Typical
28	30	0.600	15 - 40	20
35	40	0.425	30 - 60	42
65	70	0.212	65 - 90	78
100	100	0.150	80 - 98	88

### Physical Properties

Parameter	Typical
Bulk Density (Loose)	
- lb/ft <sup>3</sup>	95
- kg/m <sup>3</sup>	1528
Angle of Repose	33 Degrees

### Sizing Characteristics

Parameter	Typical
Size Guide Number (SGN)	35
Uniformity Index (UI)	12

Please refer to the Safety Data Sheet (SDS #: IMC 260001) for additional information ([www.kmag.com](http://www.kmag.com))

The information contained in this data sheet is a representation of the average properties of product analyses as tested on composite samples and typical analyses should not be considered a guaranteed specification. Individual shipment and grab sample analyses may fall outside of the above typical values. Additional handling, transportation, or improper/extended storage may affect product analyses. International Minerals Carlsbad Inc. disclaims any responsibility or liability for any loss or damage that may occur from any reliance on, or other use of, the above information with respect to the product.